

EUROPEAN COMMISSION

SEVENTH FRAMEWORK PROGRAMME

FUEL CELLS AND HYDROGEN JOINT UNDERTAKING (FCH JU)

THEME SP1-JTI-FCH.2013.3.5

Field demonstration of large scale stationary power and CHP fuel cell system

GA No. 621256



Demonstration of a combined heat and power 2MWe PEM fuel cell generator and integration into an existing chlorine production plant

Deliverable No.	DEMCOPEM-2MW D6.4	
Deliverable Title	Report on MEA failure causes with recommendations for future product and process improvements	
Dissemination level	Confidential	
Written By	Paddy Hayes (JMFC)	December 2018/Jan 2019
Checked by	Jorg Coolegem (NFCT)	Feb 2019
Approved by	Ton Pichel (Nouryon)	Feb 2019
Issue date	18 Feb 2019	

Publishable summary

Johnson Matthey Fuel Cells delivered 27,000 MEAs to equip the 2MWe DEMCOPEM power plant at the Ynnovate chlor-alkali plant in Yingkou, China.

This report describes the completion of Task 6.4, *MEA failure causes with recommendations for future product and process improvements*. MEAs returned from the Yingkou power plant were tested, examined and analysed to assess reversible and irreversible decay mechanisms. The report concludes that several separate degradation mechanisms are operating, with some influence from entrained contaminants from the chlor-alkali plant and neighbouring industries, alongside cathode catalyst dissolution and redeposition, leading to surface area loss. These degradation mechanisms could be mitigated by filtering and scrubbing reactants and coolants, and measures to limit the time the cathode spends at high potential.

In parallel with these efforts, several prototypes of improved MEAs were tested for their potential to reduce the total cost of fuel cell power plant ownership. Two designs were produced on high-volume production equipment to provide quantities sufficient for stack testing by Nedstack FCT in WP7; these consisted of a MEA with the same electrodes as the DEMCOPEM-2MW MEAs with a next generation 30µm membrane electrolyte, and a catalyst coated membrane-type MEA with a reduced platinum content and the same new membrane electrolyte. Testing has shown that the next generation membrane electrolyte is significantly more durable to common fuel cell degradation mechanisms.

6 Acknowledgment

This project is co-funded by the 7th FP (Seventh Framework Programme) – Fuel Cells and Hydrogen Joint Undertaking

<http://www.fch-ju.eu/>

<http://ec.europa.eu>



Disclaimer

The FP7 project has been made possible by a financial contribution by the European Commission under Framework Programme 7. The Publication as provided reflects only the author's view.

Every effort has been made to ensure complete and accurate information concerning this document. However, the author(s) and members of the consortium cannot be held legally responsible for any mistake in printing or faulty instructions. The authors and consortium members retrieve the right not to be responsible for the topicality, correctness, completeness or quality of the information provided. Liability claims regarding damage caused by the use of any information provided, including any kind of information that is incomplete or incorrect, will therefore be rejected. The information contained on this website is based on author's experience and on information received from the project partners.